

technical data sheet

EN

Product specifications

3-layer oak wood flooring	EN 14342	DoP PQ2025-15
Dimensions	Plank	600 x 120 x 14/ 3 mm
	Box	20 planks / 1.44 m ² / 10.70 kg
	Nested lengths	-
Density	Pallet	56 boxes / 80.64 m ² / 630 kg
	EN 323	+/- 530 kg/m ³
	Installation	T&G (glued)
Top layer		3 mm european oak (Quercus robur / Quercus petraea)
Grading		Rustic A
Surface		Slightly brushed
Bevel		Bevel 4V
Gloss level	60°	5-6%
Finishing		Oil
Warranty conditions	Residential use	20 years
	Commercial use	upon request
Application	EN 13489	Class 23



Product properties

Property		Test method	min. req.	result
Indoor air certifications				A, REACH
Fire resistance		EN 13501-1		Dfl-S1
Slip resistance		CEN/TS 15676		Dry 100, Wet 43
Formaldehyde emission		EN 717-1	≤ 0.124 mg/m ³	E1
Pentachlorofenol content		CEN/TR 14823	< 5 ppm	< detectable limit
Underfloor heating		EN 12664	R < 0.15 m ² K/W	R = 0.13 m ² K/W OK (max +28°C) + glued
Biological durability				Class 1

Cleaning and maintenance instructions: www.lamett.eu

Rustic A

EN

Grading description

Texture	Slightly brushed
Grading	Rustic
Colour variation	Medium
Sound knots	Allowed unlimited, Ø < 45 mm
Unsound knots	Allowed unlimited, Ø < 35 mm
Bark	Filled; < 5 mm width, < 40 mm length
Sapwood	< 30% of the width
End crack	< 3 mm wide, < 200 mm long
Surface crack	< 5 mm wide, < 200 mm long
Insect hole	Not allowed
Decay	Not allowed
Blue/yellow stain	Not allowed
Sound heart	Not allowed
Machine marks	Not allowed



This picture is an indication of the grading as described.

Grading description — 2 criteria

Knots

Scale from (rigid) parquet without knots up to planks with more and larger knots



Colour variation

From little colour variation/sapwood to bigger colour variation/sapwood

