

Tana 190

technical data sheet

EN

Product specifications

Multilayer parquet	EN 13489	DoP PQ2022-9
Size	Plank	190 x 400-1900 x 14(3) mm
	Box	6 planks / 2,166 m ² / 20,62 kg
	Full planks	5
	Pallet	50 boxes / 108,3 m ² / 1031 kg
Density	EN 323	± 650 kg/m ³
Installation		Tongue & Groove
Top layer		European oak (Quercus robur)
Core		Eucalyptus (Eucalyptus spp.)
Counter balance		Poplar (Populus euramericana)
Grading		Rustic AB+
Texture		Slightly Brushed
Bevel		4V
Gloss level at 60°		5 %
Finishing		UV Matt Lacquer
Warranty conditions	Residential warranty	20 years
	Commercial warranty	upon request
Use class	EN 13489	Class 23 Heavy domestic use 

Product properties

property	test method	min. req.	result
Indoor air certifications			REACH, A
Reaction to fire	 EN 13501-1		Dfl-s1
Slip resistance	 CEN/TS 15676		SRV "dry" 50
Formaldehyde emission	 EN 717-1	≤ 0.124	E1
Pentachlorophenol content	 CEN/TR 14823	< 5 ppm	Does not contain pentachlorophenol
Underfloor heating	 EN 12664	R < 0.15 m ² K/W	R= 0.11 OK (max +28°C) + glued
Biological durability			Class 1

Cleaning and maintenance instructions: www.lamett.eu



Tana 190

Rustic AB+

EN

Grading description

Texture	Slightly Brushed
Grading	Rustic
Colour variation	Medium - High
Sound knots	Allowed; $\varnothing \leq 60\text{mm}$
Unsound knots	≤ 2 per plank; $\varnothing \leq 40\text{mm}$
Sapwood	$< 20\%$ of the width
End crack	≤ 2 per plank; $< 3\text{mm}$ wide, $< 200\text{mm}$ long
Surface crack	Allowed
Insect hole	Not allowed
Decay	Not allowed
Blue/yellow stain	Not allowed
Sound heart	Not allowed
Machine marks	Not allowed



This picture is an indication of the grading as described.

Grading description

Scale from (rigid) parquet without knots up to planks with more and larger knots



From little colour variation/sapwood to bigger colour variation/sapwood

